

KIMIA O-714

Technical data sheet



www.kimioresin.com

Unsaturated polyester resin

Orthophthalic Polyester Resin

Product Description:

Kimia O-714 is an un-promoted orthophthalic based unsaturated polyester resin with low color, medium viscosity and good mechanical properties for ambient temperature cure with MEK peroxide.

Characteristics and Advantages:

- Low color
- Medium viscosity
- Good mechanical properties
- Good adhesion to glass fibers

Uses:

- Hand lay-up
- Sheet fabrication
- General purpose applications

Technical Properties:

Physical data in a liquid state at 25°C

Properties	Unit	Value	Test method
Appearance	NA	clear	NA
Color	Gardner	Max 1	ASTM D1544
Viscosity (at 25°C)	mPa.s (cP)	280-480	ISO 2555
Density (at 23°C)	g/cm ³	1.1477	ASTM D1475
Acid number	mg KOH/g	Max 22	ASTM D1639
Solid content	wt%	64±2	ASTM D1259
Gel time*	min	12-18	ASTM D2471
Curing time	min	20-35	ASTM D2471
Peak exothermic temperature	°	Max 190	ASTM D2471
Water absorption	wt%	Max 0.3	ISO 62
Flash point (open cup)	°	2	ASTM D92

This information is continuously measured and considered a part of the product's technical specifications, and their presence is only for a better description of the product.

Office : Unit 5, second floor, Shohada building,
on the corner of Karkhane Ghand cross road,
Karaj city, Alborz provience.. Iran
Factory : SH Block, Talashgaran Alley koshesh AVE,
kowsar industrial Zone. Karaj city, Alborz provience.. Iran
Tel: . +982632772130-32

WWW.MANAPAR.COM

KIMIA O-714

Technical data sheet



www.kimioresin.com

Typical non-reinforced casting properties

Tensile strength	MPa	Min 50	ISO 527-2
Tensile elongation	%	11.26	ISO 527-2
Tensile modulus	MPa	293	ISO 527-2
Flexural strength	MPa	Min 95	ISO 178
Flexural modulus	MPa	1387	ISO 178
Heat distortion temperature (HDT)	°C	Min 55	ASTM D648
Hardness (Barcol)	NA	Min 35	ASTM D2583
Linear shrinkage ($\Delta L/L$)	%	Max 1	ASTM D2566

The usual protective measures employed during the handling of Unsaturated Polyester Resins should be observed. Further product safety information can be obtained from our Material Safety Data Sheet which is available on request.

Packaging: 200 kg (net) in steel drums

Storage: Store in a cool place below 25 °C and away from moisture and direct sunlight. Under the above-mentioned storage conditions, the shelf life of the resin will be at least 6 months ex-works.

Office : Unit 5, second floor, Shohada building,
on the corner of Karkhane Ghand cross road,
Karaj city, Alborz province.. Iran
Factory : SH Block, Talashgaran Alley koshesh AVE,
kowsar industrial Zone. Karaj city, Alborz province.. Iran
Tel: . +982632772130-32

WWW.MANAPAR.COM